leipa packaging paper

# LEIPA Classic White C

is an uncoated white top testliner based on 100% recycled waste paper. The higher strength gives your product an extra stability and is underlined by a higher surface quality, what guarantees a brilliant printability.

Valid from Dezember 2021

| | | | Target Figures | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Properties | Unit | Standard | 20.5# | 22.6# | 23.6# | 24.6# | 25.6# | 26.7# | 27.7# | 28.7# | 30.8# | Tolerances |
| Grammage | g/m² | ISO 536 | 100 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 150* | ± 2% |
| Moisture | % | ISO 287 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | ± 1 |
| Burst resistance | kPa | ISO 2758 | 170 | 190 | 195 | 200 | 210 | 220 | 230 | 240 | 250 | -5% |
| SCT (CD) | kN/m | ISO 9895 | 1,2 | 1,4 | 1,4 | 1,5 | 1,6 | 1,7 | 1,8 | 1,9 | 2,0 | -5% |
| $Cobb_{60}$ TS | g/m² | ISO 535 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | 35 | ≤ 50 |
| Brightness TS | % | ISO 2470-2 | 72 | 72 | 72 | 72 | 72 | 72 | 72 | 72 | 72 | -2 |
| Roughness (Bendtsen) TS | ml/ min | ISO 8791-2 | 300 | 300 | 300 | 300 | 300 | 300 | 300 | 300 | 300 | ≤ 350 |

**preliminary*


Are you interested?
Please contact us:

e. sales@leipa.com
t. +49 3332 24-3000


www.leipa.com

## Certifications

FSC www.fsc.org FSC® C089451
The mark of responsible forestry

PEFC PEFC/04-31-0619
Promoting Sustainable Forest Management
www.pefc.co.uk

## Carbon footprint

| | DE | Europe | USA |
|---|---|---|---|
| Results by transport scenario [kg $CO_2$e/ton of paper] | 793,6 | 807,7 | 942,8 |

*Based on the EURO-GRAPH/ CEPI framework*